



CVG

Product	Saturation Magnetization $4\pi M_S$ (gauss)	Dielectric Constant ϵ'	Loss Tangent $\tan\delta_\epsilon$ ($\times 10^{-4}$)	Resonance Linewidth ΔH @3dB (oe)	Curie Temperature T_C ($^\circ C$)
---------	--	---------------------------------------	--	---	---

Type 1

40-1900	1900	14.2	≤ 2	12	240
CVG-1601	1600	14.3	≤ 1	10	220
CVG-1401	1400	13.9	≤ 2	10	215
CVG-1201	1200	14.3	≤ 2	10	205
CVG-1001	1000	14.3	≤ 2	10	200
CVG-931	930	14.3	≤ 1	10	190
CVG-801	800	14.1	≤ 1	10	180

Type 0

CVG-1850	1850	14.8	≤ 2	16	230
CVG-1600	1600	14.6	≤ 2	15	230
CVG-1400	1400	14.4	≤ 2	15	230
CVG-1200	1200	14.3	≤ 2	15	220
CVG-1100	1100	14.2	≤ 2	15	220
CVG-1050	1050	14.2	≤ 2	15	210
CVG-1000	1000	14.1	≤ 2	15	205
CVG-930	930	14.1	≤ 2	15	190