



Pacific Ceramics, Inc.

Garnets

Product	Saturation Magnetization $4\pi M_S$ (gauss)	Dielectric Constant ϵ'	Loss Tangent $\tan\delta_\epsilon$ ($\times 10^{-4}$)	Resonance Linewidth ΔH @3dB (oe)	Curie Temperature T_C ($^\circ\text{C}$)
---------	--	---------------------------------------	--	---	---

Cobalt Doped for High RF Power Applications Yttrium Iron Garnet

27-1780	1780	15.0	≤ 1	30	280
---------	------	------	----------	----	-----