



Pacific Ceramics, Inc.

Garnets

Product	Saturation Magnetization $4\pi M_S$ (gauss)	Dielectric Constant ϵ'	Loss Tangent $\tan\delta_\epsilon$ (x 10^{-4})	Resonance Linewidth ΔH @3dB (oe)	Curie Temperature T_C ($^{\circ}\text{C}$)
---------	--	---------------------------------------	--	---	---

Holmium Doped for High RF Power Applications Gadolinium Substituted Yttrium Iron Garnet

64-1400H	1400	15.0	≤ 1	85	280
64-1200H	1200	15.1	≤ 1	95	280