



Pacific Ceramics, Inc.

Garnets

Product	Saturation Magnetization $4\pi M_S$ (gauss)	Dielectric Constant ϵ'	Loss Tangent $\tan\delta_\epsilon$ ($\times 10^{-4}$)	Resonance Linewidth $\Delta H @ 3dB$ (oe)	Curie Temperature T_C ($^\circ C$)
---------	--	---------------------------------------	--	--	---

Holmium Doped for High RF Power Applications Yttrium Iron Garnet

39-1780H	1780	14.9	≤ 1	50	280
----------	------	------	----------	----	-----