



Pacific Ceramics, Inc.

Garnets

Product	Saturation Magnetization $4\pi M_S$ (gauss)	Dielectric Constant ϵ'	Loss Tangent $\tan\delta_\epsilon$ ($\times 10^{-4}$)	Resonance Linewidth $\Delta H @ 3dB$ (oe)	Curie Temperature T_C ($^{\circ}C$)
---------	--	---------------------------------------	--	--	--

Yttrium Iron Garnet

39-1780CX	1800	14.4	≤ 1	≤ 20	270
39-1780B	1780	14.9	≤ 1	25	280
39-1780A	1780	14.9	≤ 1	30	280